

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 0 831 542 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
25.03.1998 Bulletin 1998/13

(51) Int. Cl.<sup>6</sup>: **H01M 4/48**, H01M 4/52,  
C01G 53/00

(21) Application number: **97116578.2**

(22) Date of filing: **23.09.1997**

(84) Designated Contracting States:  
**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC  
NL PT SE**

(30) Priority: **24.09.1996 JP 274185/96**

(71) Applicant:  
**Japan Storage Battery Company Limited  
Minami-ku Kyoto-shi Kyoto (JP)**

(72) Inventors:  
• **Amine, Khalil,  
c/o Japan Storage Battery Co., Ltd.  
Kyoto-shi, Kyoto (JP)**

• **Yasuda, Hideo,  
c/o Japan Storage Battery Co., Ltd.  
Kyoto-shi, Kyoto (JP)**  
• **Fujita, Yuko,  
c/o Japan Storage Battery Co., Ltd.  
Kyoto-shi, Kyoto (JP)**


(74) Representative:  
**Grünecker, Kinkeldey,  
Stockmair & Schwanhäusser  
Anwaltssozietät  
Maximilianstrasse 58  
80538 München (DE)**

**(54) Method for producing positive active material of lithium secondary battery**

(57) Lithium compound and nickel oxyhydroxide containing a transition metal (Me) such as V, Cr, Mn, Fe, Zn and Co are suspended in water or in an organic solvent, and the solution is reacted with each other in an

autoclave by a hydrothermal method to thereby synthesize transition metal-containing lithium nickelate.

**FIG.1**



**EP 0 831 542 A1**

## Description

### BACKGROUND OF THE INVENTION

#### 1. Field of the Invention

The present invention relates to a method for producing a positive active material of a lithium secondary battery using an organic electrolytic solution, a polymer electrolyte or an inorganic solid electrolyte.

#### 2. Description of the Related Art

At present, a so-called lithium ion secondary battery using a carbon material as negative electrode, lithium cobaltate ( $\text{LiCoO}_2$ ) which is a lithium intercalation compound having a layered structure as positive electrode and an organic electrolytic solution as an electrolyte has been put into practice. This battery is used in various kinds of portable electronic appliances because it has very high energy density. Lithium cobaltate as a positive active material has several advantages such as high operating voltage 4V vs  $\text{Li/Li}^+$ ; high practical specific capacity of about 150 mAh/g; and good cyclic reversibility. However, cobalt is expensive because of limited reserve in view of natural resources. Therefore, lithium nickelate ( $\text{LiNiO}_2$ ) more cheap could be an alternative replacement to lithium cobaltate.

As similar to lithium cobaltate, lithium nickelate has a hexagonal layered structure belonging to a space group  $R\bar{3}m$ . In lithium nickelate, the potential is about 4 V vs  $\text{Li/Li}^+$  and the practical specific capacity is about 200 mAh/g which is higher than that of lithium cobaltate. When this material is used as positive electrode, however, multi-stage processes take place with the cell potential showing 4 plateaus indicating a four-phase reactions due to the occurrences of several structural transitions during charging and discharging. As a result, the electrochemical performance of the battery degraded very quickly upon cycling, for example, as reported in Solid State Ionics, 44, 87 (1990). Accordingly, although the specific capacity was of a very large value about 200 mAh/g initially, it decreases greatly upon repeated charging/discharging. In charge and discharging curves, the structural transition takes place with the presence of 4 plateaus in the potential curve.

In order to suppress the structural transition upon charging and discharging, it is effective to replace a part of nickel with another element. For example, replacement of nickel with cobalt has been reported in Chem. Express, 6, 161 (1991). In this case, a high-temperature solid phase sintering method was used in which: aqueous solutions of  $\text{Ni}(\text{NO}_3)_2$ ,  $\text{Co}(\text{NO}_3)_2$  and  $\text{LiOH}$  are mixed; and the resulting mixture is dried at 90°C in advance, and then sintered at 800°C in air. Further, replacement of a part of nickel with manganese has been reported in Solid State Ionics, 57, 311 (1992) and replacement of a part of nickel with an alkali-earth metal

(at the rate in a range of 0.05 to 0.10) such as magnesium, calcium, strontium, barium, etc. has been reported in the 36th Battery Discussion Meeting Lecture Summary, 9, 17, (1995). In any case, the fading of capacity with the charging/discharging cycle has been limited compared with the case of pure  $\text{LiNiO}_2$ . There is, however, a problem that the initial specific capacity is relatively low.

Generally, when a high-temperature solid phase sintering method is employed at about 750°C, the specific capacity density becomes low because vaporization of lithium occurs so that stoichiometrical active material cannot be obtained easily. In the solid sintering method, the sintering temperature should be lowered so as to avoid the vaporation of lithium at a high temperature. In this case, however, lithium nickelate cannot be obtained successfully. For improvement of this point, there is an effective countermeasure in which not respective salts of nickel and cobalt but a complex oxyhydroxide of nickel and cobalt is used as a starting material, for example, as described in the 36th Battery Discussion Meeting Lecture Summary, P.65 (1995). That is, although both nickel salt and cobalt salt are ordinarily divalent, both Ni and Co must be oxidized to trivalent state in order to synthesize cobalt-containing lithium nickelate represented by the composition  $\text{LiNi}_{1-x}\text{Co}_x\text{O}_2$ . The oxidation of each of Ni and Co from divalent to trivalent state cannot be achieved at a low temperature. On the contrary, if Ni and Co are provided in the form of oxyhydroxide ( $\text{Ni}_{1-x}\text{Co}_x\text{OOH}$ ),  $\text{LiNi}_{1-x}\text{Co}_x\text{O}_2$  is generated even at a low temperature of 400 to 500°C when oxyhydroxide ( $\text{Ni}_{1-x}\text{Co}_x\text{OOH}$ ) is made to react with a lithium compound because both Ni and Co are trivalent.

In the low-temperature solid phase sintering method, very high specific capacity of 190 mAh/g can be obtained when nitrate is used as the lithium compound whereas a specific capacity not higher than about 160 mAh/g can be obtained when hydroxide is used. This is because lithium nitrate is melted at a temperature of about 253°C and then reacts with oxyhydroxide easily whereas no melting takes place when lithium hydroxide is used. As described above, lithium nitrate is an excellent starting material in terms of improvement of the specific capacity but has a disadvantage since harmful  $\text{NO}_x$  gas is generated in the solid sintering process. Further, high specific capacity is obtained when a mixture gas of argon (80 %) and oxygen (20 %) is used as an atmospheric gas in the sintering process. However, in the case of air, there arises a problem that the specific capacity is reduced because lithium carbonate is generated as impurities due to the presence of carbon dioxide.

On the other hand, as a method of synthesizing a lithium secondary battery active material, there is used a so-called hydrothermal method in which a reaction can be made to progress, for example, at a low temperature not higher than 250°C and at a high pressure. The

hydrothermal method is, however, heretofore applied only to synthesis of  $\text{LiFeO}_2$  (Solid State Ionics, 79, 1369 (1995)) and synthesis of  $\text{LiMnO}_2$  (Proc. First Scientific Workshop for Electrochem. Materials, p.75 (1996)), for example, by using an iron compound and lithium hydroxide as starting materials.

As described above, the method of synthesizing lithium nickelate  $\text{LiNi}_{1-x}\text{Me}_x\text{O}_2$  partially replaced by other elements cannot simultaneously satisfy (A) high specific capacity, (B) prevention of generation of  $\text{NO}_x$  gas at the time of synthesizing and (C) use of air as an atmosphere at the time of synthesizing.

### SUMMARY OF THE INVENTION

It is an object of the present invention to provide a method for producing a lithium nickelate positive active material in which the specific capacity is large and no phase transition taking place during the cycling process.

In the method according to the present invention, a complex oxyhydroxide ( $\text{Ni}_{1-x}\text{Me}_x\text{OOH}$ ) of nickel and any transition metal other than nickel and a lithium compound is made react with each other in an autoclave at a low temperature of from  $105^\circ\text{C}$  to  $250^\circ\text{C}$  under high pressure by a hydrothermal method to thereby synthesize  $\text{LiNi}_{1-x}\text{Me}_x\text{O}_2$ .

The present invention provides a method for producing a transition metal-containing lithium nickelate, having no phase transition upon cycling at a low temperature in air and exhibiting high specific capacity. Not only this synthesizing method has an advantage that air is used without generation of  $\text{NO}_x$  but also has a very large industrial value in that the electric power consumed by an electric furnace as in the conventional high-temperature sintering can be saved greatly because this method is a low-temperature synthesizing method.

### BRIEF DESCRIPTION OF THE DRAWINGS

In the accompanying drawings:

Fig. 1 shows X-ray analysis graphs in which a line (a) exhibits the X-ray analysis of a positive active material according to the present invention and (b) exhibits a positive active material according to a conventional method; and


Fig. 2 shows a graph exhibiting charging/discharging characteristic of a positive electrode (a) according to the present invention and a positive electrode (b) according to the conventional method.

### DETAILED DESCRIPTION OF THE INVENTION

The present invention will be described in detail as follows.

When an aqueous solution of a complex oxyhydroxide and a lithium compound or a suspension of the com-

plex oxyhydroxide and a lithium compound in an organic solvent solution is put in an autoclave and heated at a temperature in a range of  $105^\circ\text{C}$  to  $250^\circ\text{C}$  while the content of the autoclave is pressurized in a range of 10 to 500 atm, lithium nickelate ( $\text{LiNi}_{1-x}\text{Me}_x\text{O}_2$ ) containing any metal other than nickel is generated relatively easily by hydrothermal reaction. In this case, the atmosphere in the autoclave does not always need an oxygen atmosphere. Further, not only the reaction can progress even in the case where a hydroxide is used as the lithium compound but also the reaction temperature is too low to generate  $\text{NO}_x$  even in the case where a nitrate is used as the lithium compound. Although the mechanism of the hydrothermal reaction has been not made sufficiently clear yet, it can be thought of that the reaction is a kind of ion exchange reaction such as



Alkali hydroxide is added to a mixture aqueous solution of nickel salt and salt of any transition metal other than nickel, such as vanadium, chromium, manganese, iron or cobalt to thereby generate a co-precipitated complex hydroxide of nickel and the transition metal other than nickel. Then, for example, alkali peroxodisulfate (alkaline solution) is made to act on the co-precipitated complex hydroxide to oxidize the co-precipitated complex hydroxide so as to obtain the complex oxyhydroxide. The transition metal content  $x$  is suitably selected to be in a range of from 0.05 to 0.5.

Inorganic salt, hydroxide or salt of any organic acid such as acetic acid, oxalic acid, citric acid, tartaric acid, propionic acid, etc. may be used as the lithium salt. Further, although water is most suitable as the solvent for the lithium salt, an organic solvent such as methanol, ethanol, acetone, acetonitrile, etc. or a mixture solvent of the organic solvent and water may be used effectively.

The thus obtained  $\text{LiNi}_{1-x}\text{Me}_x\text{O}_2$  is formed in an electrode together with carbon powder or metal powder as a conduction assisting agent and a binder by a known method. When this electrode is used as a positive electrode for a lithium secondary battery, the charging/discharging curve shows a monotonous variation of the potential indicating one phase reaction taking place. Accordingly, the cycle life is prolonged.

Examples of the present invention will be described below in detail.

#### Example 1

$\text{Ni}_{0.85}\text{Co}_{0.15}\text{OOH}$  of a complex oxyhydroxide of nickel and cobalt and an excess amount of lithium hydroxide exceeding the stoichiometry were suspended in water. The suspension was put in an autoclave. The autoclave was heated at  $170^\circ\text{C}$  for 3 days. In this case, the inner pressure of the autoclave was set in a range of

10 to 200 atm. Then, the reaction product was washed with water and dried at 90°C. An X-ray diffraction pattern of the sample thus obtained is shown as a line (a) in Fig. 1. Incidentally, for comparison, an X-ray diffraction graph of a sample obtained by a conventional high-temperature solid phase reaction method (in air at 750°C) with use of the same starting materials is shown as a line (b) in Fig. 1.

It is apparent from Fig. 1 that each of the two samples is  $\text{LiNi}_{0.85}\text{Co}_{0.15}\text{O}_2$  having a hexagonal layered structure. The lattice parameters of the sample according to the present invention were  $a = 2.877 \text{ \AA}$ ,  $c = 14.299 \text{ \AA}$  and  $v = 102.54 \text{ \AA}^3$  whereas the lattice parameters of the sample according to the conventional method were  $a = 2.871 \text{ \AA}$ ,  $c = 14.190 \text{ \AA}$  and  $v = 101.30 \text{ \AA}^3$ . The c-axis parameter of the sample according to the present invention is larger than that of the conventional sample. Therefore, in the sample according to the present invention, the interlayer distance is large so that lithium ions can be extracted and intercalated back very easily. Moreover, nickel ions are not shifted to the lithium site since the material is prepared at low temperature via ion exchange process so that phase transition hardly occurs.

Then,  $\text{LiNi}_{0.85}\text{Co}_{0.15}\text{O}_2$  obtained by the abovementioned process, 5 % of acetylene black as an electrically conductive agent and 5 % of an n-methyl-2-pyrrolidone solution (3 % concentration) of polyvinylidene fluoride as a binding agent were mixed with each other to give a paste shape. The paste was applied on an aluminum net as a current collector and then dried in vacuum at 250°C to thereby form an electrode having a size of  $25 \times 25 \text{ (mm)}$ . The cell comprising, this lithium cobaltate nickelate ( $\text{LiNi}_{0.85}\text{Co}_{0.15}\text{O}_2$ ) used as a positive electrode, metal lithium used as a counter electrode and an electrolytic solution composed of  $1 \text{ M} \cdot \text{LiClO}_4$  salt dissolved in mixed solvents of ethylene carbonate and diethyl carbonate, was tested. Incidentally, metal lithium was used as a reference electrode.

Fig. 2 shows a first-cycle charging/discharging curve of the positive electrode (a) according to the present invention and the positive electrode (b) according to the conventional method. In each case, the variation of the potential of the charging/discharging curve is monotonous. It is however apparent that the specific capacity (175 mAh/g) in the positive electrode produced by the method according to the present invention is considerably larger than that (120 mAh/g) in the positive electrode produced by the conventional method. Further, when the two electrodes were tested with the current density of  $0.5 \text{ mA/cm}^2$ , the charging end potential of 4.1 V (by reference to the lithium electrode) and the discharging end potential of 3.0 V, each of the two electrodes exhibited 98 % of the initial capacity after 50th cycle.

## Example 2

The complex oxyhydroxide  $\text{Ni}_{0.85}\text{Co}_{0.15}\text{OOH}$  in the Example 1 was replaced by nickel-manganese complex oxyhydroxide  $\text{Ni}_{0.85}\text{Mn}_{0.15}\text{OOH}$ . After sodium hydroxide was added to a mixture aqueous solution of nickel nitrate and manganese nitrate so that a complex hydroxide was precipitated, a sodium hydroxide solution of peroxodisulfate salt was added thereto thus to prepare the oxyhydroxide. Then, the nickel-manganese complex oxyhydroxide and the lithium acetate equivalent in amount to the former were dispersed in 500 ml of ethanol solution, and the dispersion was subjected to a hydrothermal reaction in an autoclave at 220°C. As a result,  $\text{LiNi}_{0.85}\text{Mn}_{0.15}\text{O}_2$  was obtained. The specific capacity of this active material was 172 mAh/g.

## Claims

1. A method for producing a positive active material of a lithium secondary battery comprising the steps of:
  - dissolving or suspending a lithium compound and a complex oxyhydroxide ( $\text{Ni}_{1-x}\text{Me}_x\text{OOH}$ ) of nickel and a transition metal (Me) other than nickel in an organic solvent or water; and
  - reacting said components in a pressurized autoclave by a hydrothermal method.
2. A method for producing a positive active material of a lithium secondary battery according to claim 1, wherein said transition metal (Me) comprises at least one of V, Cr, Mn, Fe, Zn and Co.
3. A method for producing a positive active material of a lithium secondary battery according to any one of claims 1 and 2, wherein said lithium compound comprises inorganic salt, hydroxide or organic salt of lithium.
4. A method for producing a positive active material of a lithium secondary battery according to any one of claims 1 to 3, wherein  $x$  in the formula  $\text{LiNi}_{1-x}\text{Me}_x\text{O}_2$  satisfies  $0.05 < x < 0.5$ .
5. A method for producing a positive active material of a lithium secondary battery according to any one of claims 1 to 4, wherein said organic solvent is at least one of ethanol, methanol, acetone and acetonitrile.
6. A method for producing a positive active material of a lithium secondary battery according to any one of claims 1 to 5, wherein when in said reacting step by hydrothermal method, the temperature is in the range of 105 to 250°C.
7. A method for producing a positive active material of

a lithium secondary battery according to any one of claims 1 to 6, wherein when in said reacting step by hydrothermal method, the pressure is in the range of 10 to 500 atm.

5

10

15

20

25

30

35

40

45

50

55

5

FIG.1





FIG.2





European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 97 11 6578

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP 0 730 314 A (MATSUSHITA ELECTRIC IND CO LTD) * column 7, line 1 - line 7; claim 12 * * column 4, line 19 - column 5, line 28 * ---	1,3,6,7	H01M4/48 H01M4/52 C01G53/00
A	EP 0 554 906 A (MATSUSHITA ELECTRIC IND CO LTD) * claims 6,7 * ---	1-4	
A	TABUCHI M ET AL: "Electrochemical and magnetic properties of lithium manganese oxide spinels prepared by oxidation at low temperature of hydrothermally obtained LiMnO2" SOLID STATE IONICS, vol. 89, no. 1-2, 1 August 1996, page 53-63 XP004070124 * page 54, experimental * ---	1,6,7	
A	EP 0 728 702 A (MATSUSHITA ELECTRIC IND CO LTD ;TODA KOGYO CORP (JP)) * claims 11,16; example 1 * -----	1,3,5-7	TECHNICAL FIELDS SEARCHED (Int.Cl.6)  H01M C01G
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 12 December 1997	Examiner Andrews, M
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03 82 (P04C01)